

Nitowrap FRC

High strength carbon fibre sheet wrap system for structural reinforcement

Uses

Nitowrap FRC is a structural reinforcement system for use on reinforced concrete, brickwork, steel & timber.

It can be used to strengthen columns and beams of load bearing structures specifically where improvement to shear strength and deformation properties is required. Typical applications include:

- Piers
- Columns
- Road & rail bridges
- Car parks
- Culverts
- Chimneys
- Historic structures

Advantages

- Very high strength to weight ratio
- Improves flexural strength capacity
- High chemical resistance
- Increases load carrying capacity of structure
- Low build system – minimal effect on structural dimensions
- Fast & easy installation – quick return to service
- No heavy equipment or temporary support during curing required - as compared to steel plate bonding
- Simple detailing – cut to length on site
- Corrosion resistant – no maintenance costs

Description

Nitowrap FRC is a high strength, high modulus, uni-directional, carbon fibre sheet which, when used in conjunction with a specially developed epoxy primer and resin adhesive, improves structural performance by strengthening and improving shear strength and deformation properties.

Nitowrap FRC is very easy to handle and apply on-site with minimal equipment required, allowing quick & easy reinforcement of structural members without major disruption.

Specification

Where indicated on the contract drawings, the carbon fibre sheet, consisting of uni-directional carbon fibres, providing tensile strength $>390 \text{ kgf/cm}$ and tensile modulus of $>2.35 \times 10^6 \text{ kgf/cm}^2$, shall be Nitowrap FRC supplied by Fosroc. (insert values appropriate to grade of wrap selected).

Properties

Nitowrap FRC

Grade	FRC 200	FRC300
Weight (g/m ²)	200	300
Design Thickness (mm)	0.111	0.167
Tensile Strength for Design (kgf/cm ²)	35,500	39,000
Tensile Modulus for Design (kgf/cm ²)	2.35x10 ⁶	2.35x10 ⁶
Elongation at Break (%)	1.5	1.5

Nitowrap Primer (S)

Viscosity (cps @ 20 ⁰ C):	2,000
Adhesion Strength: (JIS K 5400)	2.4 N/mm ²
Application Temperatures:	+25 ⁰ C to +35 ⁰ C
Pot Life:	45 minutes (+35 ⁰ C)

Nitowrap Encapsulation Resin (S)

Viscosity (cps @ 20 ⁰ C):	10,000
Application Temperatures:	+25 ⁰ C to +35 ⁰ C
Pot Life:	40 minutes (30 ⁰ C)
Adhesion Strength: (JIS K 5400)	2.4 N/mm ²
Compressive Strength: (ASTM D1002)	100 N/mm ²
Compressive Modulus: (ASTM D695)	2,050 N/mm ²
Tensile Strength: (ASTM D 638)	50 N/mm ²
Tensile Modulus of Elasticity (ASTM D638)	2,500 N/mm ²
Flexural Strength: (ASTM D 790)	75 N/mm ²

Nitowrap FRC

Technical support

Fosroc offers a technical support package to specifiers, end users and contractors, as well as unrivalled on site technical assistance all over the world.

Instructions for use

Surface Preparation

Concrete surfaces must be dry, flat, sound and free from debris and loose material. Surfaces must be fully cured and free from contamination. Blowholes or imperfections should be filled with Nitomortar FC.

Tolerance for flatness is 10mm maximum over a 2 m length, with no steps or formwork marks more than 0.5mm.

Surface preparation is preferably by sand/grit blasting to remove the surface laitance and expose the fine aggregate.

Corners of concrete surfaces to receive Nitowrap FRC should be ground to a min. radius of 10 mm.

Application

Ensure sufficient material, manpower & equipment to carry out the application within the pot-life of the resin.

Priming

Add Comp. B to Comp. A of the Nitowrap Primer and mix for 3 minutes using Fosroc No. 2 mixing paddle fitted to a low speed (<500 rpm) electric drill. Apply the Nitowrap Primer to the prepared, cleaned concrete surface, using a brush or roller, at the rate of 0.3 kg/m². Allow to cure for at least 12 hrs prior to application of Nitowrap FRC.

Application of Nitowrap FRC

Mix the Nitowrap Encapsulation Resin (same procedure as Primer) and apply to the substrate with a roller at the rate of:

FRC 200	100-200 g/m ²
FRC 300	200-300 g/m ²

Immediately place the pre-cut Nitowrap FRC onto the prepared substrate and push the wrap firmly into the epoxy using a hard rubber roller and remove the release paper backing. To ensure proper impregnation of the resin roll, using an impregnation roller, in a direction parallel to the fibres of the wrap.

After minimum 30 minutes, maximum 3 hours, roller apply a 2nd layer of Nitowrap Encapsulation Resin at the rate of:

FRC 200	100-200 g/m ²
FRC 300	200-300 g/m ²

In case of 2 ply applications allow at least 24 hrs curing prior to 2nd layer application.

Top and bottom overlaps are to be minimum 100mm. Side overlaps are not required.

Limitations

Nitowrap FRC should not be exposed to direct sunlight – Fosroc has a range of UV resistant coatings suitable for overcoating Nitowrap/Nitoplate products.

Estimating

Supply

Nitowrap FRC	100 m rolls
Nitowrap Primer	15 kg set (A+B)
Nitowrap Encapsulation	15 kg set (A+B)

Coverage

Nitowrap Primer	0.3 kg/m ²
Nitowrap Encapsulation Resin	
FRC 200	400 g/m ²
FRC 300	600 g/m ²

The above figures are dependent on substrate roughness and do not allow for wastage

Storage

Nitowrap FRC, Nitowrap Primer & Encapsulation Resin should be stored in covered warehouse conditions and out of direct sunlight.

Shelf life

Nitowrap FRC has a semi-permanent shelf life when properly stored.

Nitowrap Primer & Nitowrap Encapsulation Resin have a shelf life of 12 months when stored in normal warehouse conditions.

Nitowrap FRC

Precautions

Health and Safety

Nitowrap FRC is non-reactive. Protect against airborne carbon dust generated by the cutting procedure. Ensure adequate ventilation.

Nitowrap Primer & Nitowrap Encapsulation Resin should not come in contact with skin or eyes or be swallowed.

Wear suitable protective clothing, gloves and eye protection. In case of contact with skin, rinse with clean water, then clean with soap and water. Do not use solvent. In case of contact with eyes, rinse immediately with clean water and seek medical advice. If swallowed, seek immediate medical attention – do not induce vomiting.

For further information refer to the Material Safety Data Sheet.



Fosroc (Thailand)
Limited

777/9 Moo 7,
Bangplee-Tamru Road,
Bangplee Yai, Bangplee,
Samutprakarn 10540 Thailand

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

telephone:
+66 (0)2325 0913-15

fax:
+66 (0)2337 3551

email:
thailand@fosroc.com