

Silcor® 560 / Silcor 560 LS

Fast-cure, polyurethane waterproofing membrane

Product Description

A high performance, low odour, one-part, fast-curing, high solids, polyurethane elastomer waterproof membrane. It is specially formulated for easy roller application of all permanently flexible, tough, high build, long-life waterproof barriers.

Features

- Easy, fast, high build, one-coat application with brush or roller is possible
- Simple, seamless, fast-cure membrane
- Excellent chemical resistance, suitable for acid sulphate soils
- Waterproof — resists ponded water
- Permanently flexible — total adhesion
- Single-pack — no mixing, high build
- Systems for Total Project Specification

Silcor® 560 / Silcor 560 LS is a pure polyurethane elastomer. It does not contain bitumen or tar and will not bleed or stain. It is engineered to allow high build application without multi-layering and/or reinforcing mat. Design a Total Waterproofing Envelope package with waterproofing systems from GCP Applied Technologies.

Uses

- Wet Areas — bathrooms, shower trays, laundries, toilets, spas.
- External (non-exposed) — balconies, roof-decks, sill or window flashings, podiums, planters.
- Tanking — retaining walls, landscaped areas, ponds, water features, non-potable water storage.
- It can be applied to most stable surfaces — block, brick, concrete, render, timber, CFC, GRC, ALC, etc.
- Vertical and horizontal application.
 - Silcor 560 is hand applied for both horizontal and vertical application.
 - Silcor 560 LS (low viscosity) is sprayed applied for horizontal application with self-leveling feature.

Preparation

Surfaces must be sound, smooth and free from dust, laitance, loose matter, oil or other contaminants.

Concrete should be cured 28 days and render 7 days.



Use Silcor LM PU sealant to fill joints, cracks, gaps and form angle fillets to internal corners or penetrations.

Bond Breaker

Install Silcor LM PU sealant as bond breaker. Allow all detailing work to skin cure before proceeding with general membrane installation.

Application

Primer

To inhibit pin-holes and seal dusty, porous surfaces use one coat of Silcor Primer BS at 8 to 10m² / kg and allow to dry.

Use Silcor Primer BW F100 to seal any damp or green concrete. Roughen PVC or stainless steel before priming with Silcor Primer BW F100.

Application of Continuous Membrane

Apply Silcor 560 / Silcor 560 LS membrane liberally by brush, squeegee roller or airless spray. Allow to dry fully between coats. Apply to a minimum total WFT (Wet Film Thickness) of 1.8mm to achieve the required minimum DFT of 1.5mm. Apply in one or two coats. Test WFT during application using a Wet Film Thickness Gauge.

Do not use on trafficable areas.

Typical Properties

Property	Typical Value	Test Method
Colour	Black	-
Specific Gravity	1.45g / ml	-
Solid % Vol	91 ± 3	-
Cure Time - Ready for Flood Test, Tiling, Topping	48 hours	-
Tensile Strength	> 2.0MPa	ASTM D412
Elongation	> 550%	ASTM D412
Shore A Hardness	60 ± 5	ASTM D2240
Chemical Resistance	Excellent	ASTM C543

Surfacing

Allow product to cure overnight before foot traffic. Protect installed membrane from damage. If surface retains any tacky feel, access is achieved by a light broadcast of fine sand. Remove any loose materials before over-coating.

The following surfacing systems may be used after Silcor 560 / Silcor 560 LS membrane has fully cured.

• Exposed Areas

Use Silcor Top Coat 80 (non-slip or sheen finish) to provide UV stable protective finish.

• Tiles

Lay ceramic tiles on mortar bed or apply sand layer before application of suitable adhesive.

• Rigid Surfaces

Use 0.2mm polyethylene slip-sheet under concrete toppings. Lay paving slabs supported on mortar bed.

• Tanking

Cover with Bituthene® Protection Board or Hydroduct® Drainage Board from GCP Applied Technologies, followed by backfill or landscaping.

• Decorative Finishes

Use Silcor Primer BW F100 to seal surface, then apply any exterior quality acrylic paint.

Coverage

External - Balconies, decks, retaining walls and planters 1.25L (1.75kg) to 1.5L (2kg) / m²

Internal Wet Areas

Floors - 1.25L (1.75kg) to 1.5L(2kg) / m²

Walls - 0.4L (0.5kg) to 0.5L (0.7kg) / m²

Packaging

Silcor 560 / Silcor 560 LS Membrane 22kg pails

Clean Up

Use methylated spirits before curing. Exercise care when using solvent. Review all Material Safety Data Sheet (MSDS) before use.

Shelf Life

Do not store product exposed to weather and sun. When kept in a cool, dry, protected area, sealed pails have a 6- month shelf life at 25°C, 60% RH, but once opened may solidify within a few days.

Health and Safety

In case of spills and accidents, refer to the MSDS of the products or when in doubt contact your local GCP representative.

Always wear protective clothing, gloves and protective goggles when handling chemical products.

For full information, consult the relevant MSDS.

Project Specification

GCP offers a comprehensive package of quality and proven systems to meet different project and application needs. Contact your local GCP representative for further information.

gcpat.com | For technical information: asia.enq@gcpat.com

Australia 1800 855 525 New Zealand +64 9 448 1146 China Mainland +86 21 3158 2888 Hong Kong +852 2675 7898
India +91 124 402 8972 Indonesia +62 21 893 4260 Japan +81 3 5226 0231 Korea +82 32 820 0800 Malaysia +60 3 9074 6133
Philippines +63 49 549 7373 Singapore +65 6265 3033 Thailand +66 2 709 4470 Vietnam +84 8 3710 6168

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Silcor, Bituthene and Hydroduct are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2016 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140, USA

Printed in Singapore | 04/16 | 300-Silcor-98



gcp applied technologies

GRACE CONSTRUCTION & PACKAGING