

Silcor® Primer BS

Primer for elastomeric polyurethane membranes

Product Description

A fast-drying, single-pack, modified polyurethane primer for use with all polyurethane-based membranes.

Features

- Strong physical bond to substrate
- Fast-drying PU resin system
- Coating is water-resistant and protects the structure in the event of interruption by wet weather
- Promotes adhesion even in cold weather

Uses

Silcor® Primer BS is used for all Silcor polyurethane membrane and Bituthene® Mastic Membrane.

It may be applied to most rigid substrates used in construction including: concrete masonry, off-form concrete, in-situ concrete slabs and topping, shotcrete and cement render, light-weight foamed concrete, pre-cast concrete panels, compressed fibre cement sheet, metal and brick.

Preparation

Surfaces must be sound, smooth and free from dust, laitance, loose matter, oil or other contaminants.

Concrete should be cured 28 days and render 7 days.

Application

Apply one coat directly from container using brush, roller or spray. Allow primer coating to become tack-free before applying waterproof membrane. Only apply primer to substrate that will be membrane coated within 6 hours.

Apply the selected polyurethane waterproofing product from GCP Applied Technologies in strict accordance with product instructions.

NOTE

Silcor Primer BS is flammable - exercise care when using in a confined space. Use PPE and/or ventilation as appropriate, if required.

Typical Properties

Property	Typical Value
Colour	Clear
Specific Gravity	0.9-1.0g / mL
Water Resistance	Excellent
Drying Time @ 20°C	20 - 30 minutes

Any primed area not coated with membrane within 6 hours must be first wiped with Xylene. As soon as xylene has dried, reprime with a light coat of Silcor Primer BS at a rate of approximately 0.1kg / m². Any applied primer that has not been coated with membrane within 72 hours of application, must be fully removed by diamond grinding and re-primed.

Coverage

Application rate is approx 0.15kg / m² (0.15L / m²); 0.3kg / m² or more may be required for very porous concrete.

Packaging

Silcor Primer BS is packed in 17kg metal pails.

Clean Up

Use methylated spirits before cured. Exercise care and review all Material Safety Data Sheet (MSDS) before use.

Storage

Store in a cool, dry place. Unopened cans have a shelf life of 12 months at 25°C, 60% RH. Keep away from any fire hazards or ignition sources.

Health and Safety

In case of spills and accidents, refer to the MSDS of the products or when in doubt contact your local GCP representative.

Always wear protective clothing, gloves and protective goggles when handling chemical products.

For full information, consult the relevant MSDS.

gcpat.com | For technical information: asia.enq@gcpat.com

Australia 1800 855 525 New Zealand +64 9 448 1146 China Mainland +86 21 3158 2888 Hong Kong +852 2675 7898
India +91 124 402 8972 Indonesia +62 21 893 4260 Japan +81 3 5226 0231 Korea +82 32 820 0800 Malaysia +60 3 9074 6133
Philippines +63 49 549 7373 Singapore +65 6265 3033 Thailand +66 2 709 4470 Vietnam +84 8 3710 6168

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Silcor and Bituthene are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2016 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140, USA

Printed in Singapore | 03/16 | 300-Silcor-96



gcp applied technologies