



# Block B350 Top Sanded 3mm

## FULLY BONDED TORCH-ON APPLIED WATERPROOFING MEMBRANE

TECHNICAL SHEET 30/01/2023

### SMART ADVANTAGES

- Provides dimensional stability
- Excellent resistance to atmospheric agents
- Plasto-elastomeric modified bitumen
- Good elasticity and durable
- Polyester reinforcement gives mechanical strength
- Accommodates thermal stress
- Sanded finished

### DESCRIPTION

Block B350 Top Sanded 3mm is an APP (Atactic Polypropylene) elastomeric type modified based-sheet utilizing a specially formulated bituminous compound of distilled asphalt customized with selected high-grade visco-elastic polymers and inert filler.

### FUNCTIONAL CHARACTERISTICS

The Block B350 Top Sanded 3mm can be apply on

- Roof decks
- Concealed roof
- Re-waterproofing
- Toilet and Bathroom



### TECHNICAL CHARACTERISTICS

Reinforcement	Silica sand
Weight (UNI EN 1849-1)	3 kg
Cold Flexibility (UNI EN 1109)	-0°C
Tensile Strength (UNI EN 12311-1) <ul style="list-style-type: none"><li>•Longitudinal</li><li>•Transversal</li></ul>	500 N/5 cm 300 N/5 cm
Tearing Resistance (UNI EN 12310-1) <ul style="list-style-type: none"><li>•Longitudinal</li><li>•Transversal</li></ul>	30% 35%
Static Puncturing (UNI EN 12730) <ul style="list-style-type: none"><li>•on c/s</li><li>•on PSE 20 kg/m<sup>2</sup></li></ul>	L <sub>10</sub> L <sub>10</sub>
Dynamic Puncturing <ul style="list-style-type: none"><li>•on PSE 20 kg/m<sup>2</sup></li></ul> (UNI EN 12691) (UNI EN 1928) (UNI EN 1931)	I <sub>10</sub> Absolute ≥20.000

*\*Average laboratory values provided as a general guide*

*\*\*Actual field performance will depend on installation and site conditions*

### COVERAGE

Size 1 m (width) X 10 m (length): 10 m<sup>2</sup>/roll

### APPLICATION

#### SUBSTRATE PREPARATION

To ensure optimum results, the surface must be clean, dry, structurally sound, and free from contaminants, including but not limited to dust, dirt, loose particles, rust, oil, etc

#### PRIMING

Use brush or roller to prim the surface with 200-300 g/m<sup>2</sup> of Boscoseal Torch-on applicable primer, allow a drying time of 24 hours.

#### PLACING

Unroll and place the sheet membrane in its position on the surface. Re-roll the sheet without changing the given orientation. Unroll again, while heating the lower surface with a liquefied petroleum gas torch. Heating will cause surface

melting and subsequent adhesion to the primed surface. Sheet overlaps by at least 8.0 cm at the sides and 10.0 cm at the lap ends must be observed. Inspection of lap joints is necessary to ensure total adhesion. Smooth out seams with a rounded trowel.

#### REINFORCEMENT CORE

The reinforcement core is made of a composite system that includes a combination of non-woven fabric and fiberglass threads. The use of composite reinforcement system ensures good dimensional stability and excellent mechanical properties for standard applications.

#### STORAGE & SHELF LIFE

When unloading the material, avoid any abrupt impact with the ground. The rolls must be stored off the floor. Do not take up the rolls to the roof without using supporting pallets and safety equipment. Always store the rolls in upright position, preferably under shelter. In the cold season, do not stock the product at the site during night time. In case of double stacking, use a rigid separation board to spread the load.

The shelf life of Block B350 Top Sanded 3mm is 12 months if stored in a cool, dry and weatherproof environment.

#### PACKAGING

The Block B350 Top Sanded 3mm comes with sizes of 1m width X 10m length per roll

#### HEALTH AND SAFETY

For personal precautions, protective gloves and eye goggles should be worn when handling the product.

For more detailed information refer to Safety Data Sheet.

The application recommendations are defined by standards of use. They are imperative to respect them, but they don't need a previous try, especially for the first use or particular inconvenient of support, site or environment.  
Consult our safety data sheet for precautions to use.

#### DISCLAIMER


Bostik offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations.

The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bostik's research only. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contain herein.

Bostik Findley (Seremban) Sdn. Bhd.  
Lot 112 & 113, Kawasan Perindustrian Senawang,  
70450 Seremban, Negeri Sembilan DK., Malaysia.  
Phone: +606 678 9788  
www.bostik.com

**BOSTIK HOTLINE**

**Smart help +606 678 9788**



All advice, recommendations, figures and safety regulations provided are based on careful investigations, as well as the current state of our experience and are without obligation. Although the documentation has been compiled with the greatest care, we do not accept any liability for inaccuracies, mistakes, typesetting or printing errors. We reserve the right to modify the respective product if we deem it necessary. Since the design, the quality of the substrate and the processing conditions are beyond our assessment, no liability can be accepted for work performed on the basis of this documentation. We therefore advise you to carry out practical tests on site yourself. Our general Terms and Conditions of Sale and Delivery apply to all our sales and deliveries.